



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
 Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

CF726 C.C EPDM SPONGE RUBBER GREY/BLACK

PROPERTY	SPECIFICATION	TEST METHOD
Composition	EPDM	
Cell Structure	Closed	
Grade	RE42/2A2	
Density (pcf)	4 to 8	ASTM D 3574
Shore 00 Durometer	50 - 60	ASTM D 2240
25% CFD (psi)	5 to 9	ASTM D 1056
Compression Set	<35	ASTM D 1056
Tensile Strength (psi)	80	ASTM D 412 (Die A)
Elongation (%)	150	ASTM D 412 (Die A)
Tear Strength (ppi)	9.6	ASTM D 624 (Die C)
Resilience (%)	35	ASTM D 2632
Water Absorption (weight %)	5 max	ASTM D 1056
Flame resistance	Pass	FMVSS 302/UL94HF-1
Service Temperature (°F)		
Low	-70	ASTM D 746
High Continuous	220	
High Intermittent	250	

Combi-Fab can not anticipate all conditions under which this information and our products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. Unless otherwise agreed in writing, we sell the products without warranty and users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose.