



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
 Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

CF732 (60 DURO) NEOPRENE BLACK

Hardness (Shore A)		60 Durometer	ASTM D-2240
100% Modulus		340 PSI	ASTM D-412
300% Modulus		900 PSI	ASTM D-412
Tensile		900 PSI	ASTM D-412
Elongation		300%	ASTM D-412
Tear		150 lbs./in.	ASTM D-624
NBS Abrasion		25%	ASTM D-1630
Cold Temperature		-30°C	ASTM D-746
Ozone Resistance 70 Hrs/ @ 5 PPHM		no cracking	ASTM D-1171
Volume Resistivity		3.6 x 10 ¹⁰ OHM-CM	ASTM D-257
Compression set 22 Hrs. @ 100°C		31%	ASTM D-395B
Heat Aging 70 Hrs. @ 100°C			ASTM D-573
	Change	Hardness	9 Points
		Tensile	-4%
		Elongation	-21%
Oil Aging No. 3 Oil 70 Hrs @ 100°C			ASTM D-471
	Change	Hardness	-30 Points
		Tensile	-42%
		Elongation	-41%
		Mass	34%
		Volume	53%