



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8  
Phone: (905) 277-9925 | Fax: (905) 277-9934 | [www.combifab.com](http://www.combifab.com)

## TECHNICAL DATA SHEET

### **CF732 (80 DURO) NEOPRENE BLACK**

Hardness (Shore A)	80 Durometer	ASTM D-2240
100% Modulus	720 PSI	ASTM D-412
300% Modulus	1700 PSI	ASTM D-412
Tensile	2300 PSI	ASTM D-412
Elongation	370%	ASTM D-412
Tear	230 lbs./in.	ASTM D-624
NBS Abrasion	133%	ASTM D-1630
Cold Temperature	-35°C	ASTM D-746
Compression set 22 Hrs. @ 70°C	24%	ASTM D-395B
Cured @ 151°C T2	10 Minimum	ASTM D-395B
T95	22 Minimum	
Heat Aging 70 Hrs. @ 70°C		ASTM D-573
Change	Hardness	4 Points
	Tensile	-9%
	Elongation	-15%