



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

CF739 SILICONE COMPATIBLE RUBBER

Hardness (Shore A)	80 Durometer	ASTM D-2240
Tensile Strength	1500 PSI	ASTM D-412
Elongation	150%	ASTM D-412
Cold Temperature	-40°C	ASTM D-2137-K
Compression set 22Hrs. @ 70°C	25%	ASTM D-395B
Heating Aging 70 Hrs. @ 70°C Change	Hardness +10 points Tensile - 25% Elongation - 25%	ASTM D-2240 ASTM D-412 ASTM D-412
Ozone Resistance	100%	ASTM D-1171