



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

CF781 CORK COMPOSITION

Physical Characteristics

Composition Cork, with Polyurethane Binder.

Density (Minimum)	12.5 Lbs./Cub. Ft.
Tensile Strength (PSI)	Longitudinal: 70 Minimum Transversal: 45 Minimum
Compressibility (400 PSI)	20% to 40%
Recovery	70% Minimum