



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
 Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

CF/PS711-712-713 O.C. SPONGE RUBBER

Available in Sheet or Toll Form, without adhesive (CF) or with a double coated pressure sensitive film high tack rubber adhesive (PS).

Product Description	711	712	713
ASTM D-1056-78	R011	R012	R013
Density (lbs./cub.ft.)	20 +/- 2	25 +/- 2	32 +/- 2
Compression - Deflection 25% (PSI)	2 - 5	5 - 9	9 - 13
Compression Set 22 Hrs. @ 158°F 50% Deflection	-----15% Maximum-----		
% Recovery - 22 Hrs. @ 70°F	-----95% Minimum-----		
Accelerated Aging 7 Days at 158°F % Change in Compression Deflection	----- +/- 20% -----		
Ultimate Tensile Strength (type) PSI	100	95	85
Elongation (Minimum) %	250	225	200
Shrinkage Lineal After 7 Days @ 158°F	-----2% Maximum-----		
Contact Stain (ASTM D-925) Automobile Baked Enamel	-----NONE-----		
Low Temperature Flexibility	-----Flexible @ 20°F-----		
High Temperature	-----180°F Intermittent-----		
	-----160°F - Service Range-----		