



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8  
Phone: (905) 277-9925 | Fax: (905) 277-9934 | [www.combifab.com](http://www.combifab.com)

## TECHNICAL DATA SHEET

### **CF/PS873 LOW MODULUS, CELLULAR URETHANE FOAM BLACK**

*Available in sheet or roll form, Die cut parts, without adhesive (CF) or with a high tack rubber adhesive one side(PS).*

#### *Product Description*

Density (lbs./cub. ft.)	20
Compression Set (% max.) @ 73°F	2
Compression/Deflection @25% (PSI)	10
Hardness, Durometer Shore "0"	53
Tensile Strength (PSI Min)	198
Tensile Elongation (% Min.)	380
Water Absorption (% Wt. Gain Max.)	10
Temperature Resistance	
Cold Flexibility MIL-P-12420C	
@ -40°F	F
High Continuous (ASTM D746)	158°F
High Intermittent (ASTM D746)	250°F