



2537 Wharton Glen Avenue, Mississauga, Ontario, L4X 2A8
Phone: (905) 277-9925 | Fax: (905) 277-9934 | www.combifab.com

TECHNICAL DATA SHEET

PS752M CORK & RUBBER WITH AC694 ADHESIVE

Physical Characteristics

Fine granular cork, with synthetic rubber binder, (to MIL-T-6841)

Hardness (Shore A)	50-65 Durometer
Tensile Strength (PSI)	150 Minimum
Compressibility (400 PSI)	30% to 45%
Recovery	75% Minimum
Flexibility (F-5)	no cracking